

Altro Whiterock™ hygienic wall and ceiling systems



Data sheet
'EU' grade - extruded W103/104,
Altro Whiterock standard white

Economical standard grade for general purpose use.
Also suitable where sheet may come into contact
with food.

Description

Extruded semi-rigid PVCu sheet.

Colour: white

Surface finish: Satin

Thickness: 2.5mm

Size: 2500 x 1220mm (W103)
3000 x 1220mm (W104)

Weight: 3.5 kg per m²

Maximum service temp: 60°C

Altro Whiterock W103/104 PVCu extruded sheet is supplied with a protective film on its face which can be left in place until the room is ready for use. This also helps to protect the surface from dust while other trades are in the area. It is ideal for applications requiring a hygienic easy-to-clean, almost maintenance free wall finish, which conforms to UK hygiene requirements.

This is the most economical standard grade which will be used for the majority of installations.

Fixing

The sheets can be fixed directly to most dry substrates depending on its surface suitability, using one of the following methods:

1. AltroFix® W139 all over adhesive
2. AltroFix® W173 all over adhesive
3. AltroFix® W157 all over adhesive

Cutting

A jigsaw is the best method, however a fine toothed hand saw can also be used.

Jointing

- see relevant detailed drawings

1. A high impact extruded PVCu 'H' joint trim (available in two part or single part profiles), incorporating a watertight seal at the mouth of the joint, which is unique to Altro Whiterock.
2. A powder coated aluminium "H" joint used for extra impact or heat resistance.
3. Silicone joint 3-4mm wide.
4. Hot welded joint - ask for details.

Internal/external corners

- see relevant detailed drawings

Altro Whiterock is normally thermoformed on-site, so that window and door reveals are neatly clad without an edge joint. However, profiles are available for the self-installer to cope with these details. Vulnerable external corners are usually over-clad with stainless steel corner protectors, to a height of 1200mm.

Cleaning

Regular cleaning using a soft cloth and a suitably diluted mild detergent is all that is normally required. Stubborn marks can be removed with Altro Cleaner A859 or non-abrasive domestic type cream bath cleaner.

Do not use abrasive pads or wire wool.

Do not clean above 60°C.

Cleaning cards are available on request.

Chemical resistance

Resistant to a wide range of chemicals, specific details on request.

Availability

Ex-stock

Storage & conditioning (on-site)

Sheets should be stored flat, fully supported and left for 24 hours to attain the ambient room temperature prior to installation (min 14°C).

Limitations of use

Altro Whiterock W103/104 has a maximum working temperature of 60°C. For temperatures above this use stainless steel. Stainless steel must be used for all open flame areas (available cut to size). If a layout showing the position of equipment can be supplied, we will provide specific advice as to the best combination of materials to use.

Typical applications

- Commercial kitchens
- Laboratories
- Pharmaceutical areas
- Food manufacturing areas
- Shower/toilet/changing room areas

Our Technical Services Department is available for advice on 01502 561364.

Technical data

| Property | DIN | Values |
|---|-------------------------|----------------------------------|
| Density (g/cm ³) | ISO 1183 | 1.39 |
| E-modulus of elasticity (Mpa) | ISO 527 | 3550 |
| Impact resistance (KJ/m ²) | ISO 179/1eU | |
| +20°C | | Without rupture |
| 0°C | | Without rupture |
| -20°C | | Without rupture |
| Flexural strength (Mpa) | ISO 178 | 79.8 |
| Tensile strength (Mpa) | ISO 527 | 48 |
| Shore-hardness D | ISO 868 | 79 |
| Surface resistance ROE (Ω) | DIN IEC 60 167 | 2.00E +14 |
| Volume Resistance RD (Ω) | DIN IEC 60 093 | 6.90E +13 |
| Dielectric strength (kV/mm) | DIN IEC 243 | 16.8 |
| Dielectric constant | 53483 | 3.2 |
| Dielectric loss index | 53483 | 0.02 |
| Thermal conductivity - 'K Value' (W/mK) | 52612 | 0.16 |
| "U" value (bonded to 100mm block wall (W/m ² °C) | 52612 | 1.8 |
| Expansion coefficient at 20°C after 1 h storage at 90°C (10 ⁴ /K) | 53752 | 7.10 ⁻⁵ |
| Compressive strength (N/mm ²) | 53454 | 70 |
| Vicat softening point VST/B (°C) | ISO 306 | 80 |
| Heat distortion temperature (°C) | ISO 75-2 | 60 |
| Water absorption (%) | ISO 62 | 0.09 |
| Moisture vapour transmission rate (MVTR) | ASTME96 | 0.120 g/m ² /24hrs |
| Water vapour resistivity | ASTME96 | 3.82 x 10 ⁵ GN.S/Kg.m |
| Light reflectance values (LRV) | D65 artificial daylight | 95 |
| Flammability | | |
| Surface spread of flame | BS 476 Part 7 1987 | Class 1 |
| Fire propagation | BS 476 Part 6 1989 | Class 0* |

(*when fixed to a non-combustible substrate)

ALTO WHITEROCK™ HYGIENIC
WALL AND CEILING SYSTEMS
'EU' GRADE - EXTRUDED W103/104,
ALTO WHITEROCK STANDARD WHITE

for further information or technical advice

tel: 01502 561364 fax: 01502 531461

e-mail: walls@altro.com or explore www.altro.com